



Cellulose-Based Materials as a Sustainable Alternative to Plastics: Mitigating Environmental Pollution Through Biodegradability and Reduced Toxicity

B. S. Ojelade[†] , R. I. Nethanani and P. O. Adesoye

Department of Forestry, Faculty of Science, Engineering and Agriculture, University of Venda, Thohoyandou 0950, Limpopo, South Africa

[†]Corresponding author: B.S. Ojelade; babatunde.ojelade@univen.ac.za

Abbreviation: Nat. Env. & Poll. Technol.

Website: www.neptjournal.com

Received: 26-04-2025

Revised: 09-07-2025

Accepted: 12-07-2025

Key Words:

Cellulose-based materials
Microplastic pollution
Ecosystem toxicity
Green chemistry
Sustainable alternatives

Citation for the Paper:

Ojelade, B.S., Nethanani, R.I. and Adesoye, P.O., 2026. Cellulose-based materials as a sustainable alternative to plastics: mitigating environmental pollution through biodegradability and reduced toxicity. *Nature Environment and Pollution Technology*, 25(1), D1808. <https://doi.org/10.46488/NEPT.2026.v25i01.D1808>

Note: From 2025, the journal has adopted the use of Article IDs in citations instead of traditional consecutive page numbers. Each article is now given individual page ranges starting from page 1.



Copyright: © 2026 by the authors

Licensee: Technoscience Publications

This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

ABSTRACT

This review examines the potential of using cellulose materials for overcoming environmental issues such as pollution, microplastics, and ecological toxicity as sustainable alternatives to petroleum-based plastics. Unlike plastics, which persist in the environment and break down into microplastics, cellulose materials readily degrade into non-toxic organic compounds, thus reducing pollutants in soil and water. The review outlines the relatively low environmental impact of cellulose production from renewable materials such as timber, agricultural waste, and non-timber flora. Cellulose, unlike petroleum-based polymers, is produced with lower energy inputs, greenhouse gas emissions, and greater carbon capture during plant growth. Sustainably harvested and farmed cellulose strengthens its circular economy relationship, clocking in with boastful compostability, and in some instances, recyclability. The described processes, including the manufacture of nanocellulose, chemically and mechanically treat the cellulose, improving its strength, flexibility, moisture resistance, and expanding its application in packaging, biocomposites, textiles, and medical devices. There are still some disadvantages, such as high costs, lack of industrial composting, and absence of enabling legislation. The review calls for greater advocacy of policy change, technological improvements, and public awareness campaigns aimed at promoting the use of cellulose. Most importantly, it demonstrates why these materials are needed to reduce pollution inflicted by plastics, protect biodiversity, enhance sustainability, and manage waste through responsible consumption.

INTRODUCTION

The origin of plastics dates back to the early 20th century, when they were introduced as substitutes for natural materials like ivory, horn, and tortoiseshell (Andrady & Neal 2009, Gilbert 2017). With the invention of synthetic polymers such as Bakelite in 1907 and the development of petroleum-based plastics in the 1950s, plastics quickly became integrated into modern society due to their moldability, durability, lightweight, and cost-efficiency (Thompson et al. 2009, Geyer et al. 2017). Today, plastics are indispensable across various sectors, including packaging, electronics, textiles, automotive, and healthcare. Global plastic production has grown from 2 million tonnes in 1950 to over 390 million tonnes in recent years, underscoring its widespread acceptance and utility (PlasticsEurope 2021). Their chemical resilience and ability to meet specific functional needs at low costs have made plastics central to modern industrial and consumer applications.

However, the rapid proliferation of plastics has created far-reaching environmental, health, and socioeconomic consequences. Plastics are primarily derived from non-renewable fossil fuels and are largely non-biodegradable, persisting in ecosystems for hundreds of years (Jambeck et al. 2015). Each year, approximately 8 million metric tonnes of plastic waste enter the oceans, contributing to global environmental degradation (Lebreton et al. 2017). Approximately 79% of plastic waste is in landfills or the natural environment, while only 9% is recycled

(Geyer et al. 2017). Weathering and degradation processes fragment plastics into microplastics (<5 mm), which are now detected in marine organisms, soils, food, water, and even human tissues (Jambeck et al. 2015). Furthermore, plastics can leach toxic additives such as phthalates and bisphenol A (BPA), which are associated with endocrine disruption, developmental abnormalities, and increased risks of cancer and reproductive disorders in humans and wildlife (Godswill & Godspel 2019). In food systems, plastics compromise safety by leaching into food products, especially under high temperatures or acidic conditions (Groh et al. 2019, Obuzor & Onyedikachi 2023). Despite these well-documented risks, global responses remain inadequate. Many policy interventions are still nascent or inconsistently enforced, while sustainable alternatives have yet to achieve widespread adoption (Giacovelli 2018).

In light of these concerns, cellulose, a naturally abundant, biodegradable polymer derived from plant cell walls, has attracted renewed attention as a viable substitute for petroleum-based plastics. Sourced from wood, agricultural residues, and lignocellulosic biomass, cellulose is the most prevalent biopolymer on Earth (Klemm et al. 2005, Mujtaba et al. 2023). Unlike synthetic polymers, cellulose and its derivatives are compostable, less toxic, and derived from renewable resources (Maraveas 2020a). Technological advancements have significantly enhanced the material properties of cellulose. For instance, nanocellulose—produced via mechanical or chemical disintegration of cellulose fibres—exhibits superior strength, barrier properties, and flexibility, making it suitable for packaging, biomedical devices, and composites (Dufresne 2013, Shaghaleh et al. 2018). Additionally, specific chemical changes like acetylation have resulted in derivatives such as cellulose acetate, which improves resistance to water and durability, therefore broadening its application scope in coatings, films, and fibres (Habibi et al. 2010, Shaghaleh et al. 2018). Recent studies underscore the environmental advantages of cellulose-based alternatives, particularly in reducing microplastic generation, toxic leachates, and carbon footprints associated with plastic lifecycle emissions (Foroughi et al. 2021, Jing et al. 2024).

This review analyzes the possibilities of cellulose-containing materials as substitutes for plastics of environmental impact, characteristics of materials, technologies for processing materials, and economic aspects. It highlights current innovations, identifies the regulatory and market challenges impeding widespread adoption, and provides a comparative assessment of biodegradability, toxicity, and life cycle sustainability. The findings are relevant to stakeholders such as scientists, policymakers,

business professionals, and eco-organizations targeting the shift towards sustainable materials. This review is distinctive in its holistic evaluation of cellulose-based biomaterials as potential substitutes for plastics. Beyond characterizing the materials, it assesses the recent technological developments, biodegradation, toxicity, and life cycle impacts of cellulose-based plastics. Moreover, the review examines regulatory, market, and economic obstacles that inhibit widespread adoption; these factors are often neglected by other studies. This integrative approach enhances cross-sectoral efforts to propose meaningful innovations, policies, and marketing strategies aimed at harnessing cellulose composites to alleviate plastic pollution.

ENVIRONMENTAL PERSISTENCE AND BIODEGRADABILITY

Functional Comparison of Plastics and Cellulose-Based Materials Across Industrial Applications

Plastics and cellulose-based materials serve as two distinct material classes—synthetic and fossil-derived, the other natural and bio-based—yet both have played transformative roles in industrial development. An integrated overview of their applications and functions aids in understanding the material shift currently in relation to environmental sustainability (Table 1). Due to their ease of use, cost-effectiveness and barrier properties, plastics form the bulk of the packaging industry (Wu et al. 2021). Polypropylene (PP), Polyethylene (PE), and polyethylene terephthalate (PET) are popular for food containers, films and bottles owing to their gas and moisture impermeability, which preserves the product's quality (Wu et al. 2021). However, the long-lasting durability of these materials results in waste. On the other hand, paper, nanocellulose films, and cellulose acetate are more cellulose-based materials that are increasingly being researched for use in packaging (Romão et al. 2022, Yekta et al. 2023, Ren et al. 2024). Though traditionally limited by poor moisture resistance, recent coatings and chemical modification innovations have significantly enhanced their barrier properties, making them competitive in short-lifespan applications.

Due to their strength and chemical resistance, plastic materials like PVC and polystyrene are used in piping, insulation, and fittings (Revuelta 2021). Cellulose-based boards and bio-composites are gaining traction as eco-friendly alternatives in interior cladding, insulation, and lightweight construction panels (Saini & Ledwani 2024). While not yet mainstream for heavy-duty infrastructure, modified cellulose offers advantages in biodegradability, indoor air quality, and renewable sourcing.

Plastics reduce vehicle weight, enhancing fuel efficiency. ABS, nylon, and composites are used in vehicle interiors, exterior trims, and under-hood components (Gupta & Singhal 2022). Cellulose-reinforced composites (e.g., nanocellulose-polymer blends) are emerging as substitutes in dashboards, door panels, and insulation layers (Karak 2024, Carvalho et al. 2024). Though still under development, they provide comparable mechanical strength with significantly reduced environmental footprints.

Plastics are vital in healthcare for sterile, disposable items such as syringes, IV bags, and diagnostic equipment (Greene et al. 2022). Biocompatible and biodegradable cellulose is used in wound dressings, drug delivery systems, and biosensors (Khan et al. 2024). Nanocellulose hydrogels and scaffolds are being actively researched in tissue engineering (Tamo 2024). However, challenges remain in ensuring sterility, mechanical strength, and cost-competitiveness for wide clinical deployment.

Plastics are used in greenhouses, mulch films, irrigation systems, and silage wraps (Maraveas 2020b). While effective, their disposal contributes to soil and microplastic contamination. Biodegradable cellulose-based films and coatings derived from agricultural waste are being developed to support controlled release, moisture retention, and compostability, thus offering circular economy advantages (Giordanengo 2024, Riseh 2024).

Synthetic fibres like polyester and nylon dominate textiles, offering strength and flexibility but contributing significantly to microplastic pollution. Cellulose-based

alternatives, such as lyocell, modal, and viscose, are already commercialized and provide renewable, biodegradable options (Wang et al. 2021). These materials are widely used in fashion, upholstery, and hygiene products, though water and chemical use in production must be optimized.

Biodegradability of Plastics and Cellulose-Based Materials in Different Environments

Plastic and cellulose-based material degradation rates vary greatly by environment (Table 2). Traditional petroleum-derived plastics like polyethylene and polypropylene can persist in landfills for years due to their resistance to microbial activity and climatic conditions (Raddadi & Fava 2019). Due to photodegradation, UV radiation converts these plastics to microplastics without mineralizing them, slowing their breakdown in marine settings (Gewert et al. 2015). Certain plastics, including polyvinyl chloride (PVC), withstand environmental deterioration and degrade slowly in soil (Hopewell et al. 2009).

Cellulose degrades faster than plastic (Yaradoddi et al. 2020). The cellulose breaks down within weeks to months under certain conditions (Azwa et al. 2013). According to Erdal & Hakkarainen (2022), cellulose breaks down in composting in three to six months. Briassoulis et al. (2019) found that bacteria may destroy cellulose sheets in seawater after a few months. Abiotic degradation of cellulose occurs in the soil as bacteria and fungi transform cellulose into glucose, subsequently converting it into carbon dioxide and water (Datta 2024).

Table 1: Comparison of typical plastic applications and corresponding cellulose-based alternatives.

Application Sector	Typical Plastic Materials	Cellulose-Based Alternatives	Remarks
Packaging	PE, PP, PET, PS	Cellulose films, nanocellulose coatings, cellulose acetate	Improved barrier properties through functionalization/coating
Textiles	Polyester, Nylon, Acrylic	Lyocell, Modal, Viscose	Derived from regenerated cellulose, biodegradable but chemical-intensive
Healthcare	PVC, PP, PET, ABS	Cellulose hydrogels, nanocellulose scaffolds, biofilms	Suitable for wound dressings, drug delivery, sterility remains a challenge
Construction	PVC, Polystyrene, Polycarbonate	Cellulose composites, fiberboards, insulation panels	Offers a renewable alternative for interior applications
Automotive	ABS, PP, Nylon, composites	Cellulose-reinforced composites, nanocellulose-polymer hybrids	Emerging use in lightweight panels and trims
Electronics	ABS, PC, HIPS	Transparent nanocellulose films, flexible substrates	Early-stage development, potential in green electronics
Agriculture	PE films, PP containers	Biodegradable cellulose mulch films, coated cellulose packaging	Supports compostability and moisture retention
3D Printing & Bioplastics	PLA blends, ABS	Cellulose-PLA composites, cellulose acetate filaments	Enhancing printability and biodegradability in additive manufacturing
Cosmetics & Personal Care	Microbeads in gels, PE containers	Cellulose microbeads, molded pulp packaging	Replacing banned plastic microbeads, improving sustainable packaging

Enzymes and bacteria generally facilitate cellulose breakdown. Bacteria and fungi synthesize cellulases and hemicellulases that decompose cellulose polymers into smaller units such as cellobiose and glucose (Lynd et al. 2002, Datta 2024). In rich soil and compost, these bacteria break down cellulose into organic molecules to synthesize necessary organic chemicals (Datta 2024). Zeghal et al. (2021) observed that marine bacteria and fungi increase cellulose degradation. By degrading cellulose into glucose, microbes get energy. Synthetic plastics decompose slowly in microbiological breakdown processes because they resist enzymatic activity (Gewert et al. 2015).

Studies have shown that cellulose degrades differently from plastics (Puls et al. 2011, Grzybek 2024). Slezak et al. (2023) found that cellulose-based biodegradable film degraded after six months when buried in soil, whereas plastic films did not after a year. Cellulolytic marine microorganisms break down cellulose-based materials fast, whereas plastics endure for years (Briassoulis et al. 2019). Polylactic acid (PLA) takes approximately twice as long to break down in composting as cellulose acetate (Tsuji 2013).

Cellulose is more biodegradable than conventional and certain bioplastics. Polar ice and deep-sea sediments

contain microplastics, according to Thompson et al. (2004). Moreover, these microplastics do not degrade; instead, they fragment, leading to enduring pollution. Consequently, plankton, fish, and humans have ingested them, potentially posing health hazards and changing food chains (Rochman 2018). Conversely, cellulose-based products decompose into organic chemicals that are environmentally benign. Cellulose particles are quickly metabolized by bacteria, reducing their long-term build-up in ecosystems. Thus, cellulose is considerably less detrimental to natural ecosystems.

Impact on Ecosystems (Terrestrial and Aquatic Organisms)

Plastics negatively impact terrestrial and aquatic ecosystems. In urban settings, terrestrial animals may consume or become ensnared in plastic waste, leading to damage or death (Gall & Thompson 2015). Plastics have been detected in the digestive systems of numerous species, including fish, birds, and mammals, within marine ecosystems (Lusher et al. 2013). The consumption of plastics might cause physical obstructions, malnutrition, and exposure to hazardous substances, resulting in population decreases (Awuchi & Awuchi 2019, Ghosh et al. 2023). Conversely,

Table 2: Biodegradability rates and environmental impact of cellulose-based vs. petroleum-based plastics.

Material Type	Environment	Degradation Time	Influencing Factors	Environmental Impact	References
Traditional Petroleum Plastics	Soil	>500 years	Low microbial activity, slow photodegradation	High emissions, significant microplastic pollution	Andrady 2011, Gewert et al. 2015
Traditional Petroleum Plastics	Marine	>500 years	UV exposure, low biodegradation	High water use, no carbon sequestration	Thompson et al. 2004, Jambeck et al. 2015
Bioplastics (PLA)	Composting Facility	3-6 months	Elevated temperature, high microbial activity	Moderate environmental impact, reduced emissions	Tsuji 2013
Cellulose-Based Materials	Soil	1-3 months	High microbial activity, moderate moisture levels	Low emissions, positive carbon sequestration during growth	Skrzypczak et al. 2023, Salimi et al. 2024
Cellulose-Based Materials	Marine	1-3 months	Microbial degradation, moderate water conditions	No microplastic pollution, moderate water use	Briassoulis et al. 2019




Fig. 1: Environmental fates of plastics and cellulose-based materials.

cellulose-derived compounds are biodegradable and pose negligible dangers to organisms (Erdal & Hakkarainen 2022). Upon introduction into terrestrial or marine habitats, they degrade into non-toxic organic molecules, thereby diminishing ingestion and entanglement hazards while alleviating chemical contamination. Moreover, cellulose decomposition facilitates nutrient cycling in soil ecosystems, fostering microbial proliferation and enhancing soil health (Zhan 2024).

The utilization of cellulose-based materials may substantially reduce the enduring environmental hazards associated with traditional plastics (Fig. 1). Cellulose, owing to its biodegradable characteristics, does not contribute to microplastic pollution, establishing it as a sustainable alternative for packaging, fabrics, and disposable products. Shifting from petroleum-derived plastics to cellulose-based substitutes can diminish the buildup of enduring plastic waste in the environment, mitigating its detrimental impacts on ecosystems and human health (Klemm et al. 2005).

LIFECYCLE ANALYSIS OF CELLULOSE-BASED MATERIALS

Resource Extraction and Production

Impacts of cellulose sourcing from wood, plants, and agricultural residue: Cellulose, the most abundant organic polymer, comes from wood, plants, and agricultural waste. To manufacture cellulose fiber, trees, cotton, or post-harvest agricultural byproducts are pulped to eliminate lignin and other impurities (Klemm et al. 2005). Cellulose extraction can harm the environment depending on the feedstock and methods. Sustainable Forest Management can reduce habitat loss, carbon emissions, and biodiversity loss from deforestation (Condé et al. 2022). Forest Stewardship Council (FSC) accreditation supports responsible forest management to prevent environmental deterioration from cellulose extraction from wood (Cashore et al. 2006). Instead of throwing away or burning sugarcane bagasse or straw, reusing them saves the environment. These leftovers add to greenhouse gas emissions and energy usage during transit and processing (Joshi et al. 2015). Cellulose extraction leaves less carbon footprint than petroleum-based polymers because it is ecologically benign and uses plant-based raw materials that store carbon during growth (Rajendran et al. 2025).

Compared to fossil-based plastics, cellulose extraction has a substantially lower carbon footprint (Foroughi et al. 2021). Producing 1 kg of bleached kraft pulp emits approximately 0.3–0.6 kg CO₂-eq, while polyethylene and polypropylene production emit 1.8–2.5 kg CO₂-eq per kg (Kim et al. 2022). Cellulose-based materials can also

sequester 1.75–12.3 tons CO₂ per hectare per year through carbon storage during plant growth (Kim et al. 2022, Forfora et al. 2024).

Energy, water, and emissions comparison with petroleum-based plastics: Refining crude oil and natural gas produces polyethylene and polypropylene. Due to their energy usage, these activities increase greenhouse gas emissions and global climate change (Hopewell et al. 2009). Making plastic polymers from crude oil requires a lot of water and energy. Virgin polyethylene production consumes 80–90 MJ/kg primary energy, far exceeding the 30–50 MJ/kg required for cellulose-based products (Schirmeister & Mülhaupt 2022, Ritzen et al. 2024). However, cellulose manufacturing consumes less energy and emits fewer greenhouse gases. According to Van Schoubroeck et al. (2018), cellulose and other bio-based products have less impact on the environment in terms of non-renewable energy usage and global warming. However, processing cellulose in big pulping facilities may be energy and water-intensive. Kraft pulping can consume 30–60 m³ of water per tonne of pulp, generating effluents that, if poorly treated, cause water pollution (Badar & Farooqi 2012, Latha et al. 2018).

Use Phase and Performance Comparison

Cellulose-Based Products: durability, performance, and usability: Cellulose is used in construction, biomedical devices, textiles, and packaging (Felgueiras et al. 2021). Cellulose products are useful and frequently endure a long time; however, petroleum-based polymers may perform better (Wang et al. 2021). Cellulose-based packaging materials lack polyethylene in water resistance and tensile strength (Wang et al. 2021). Aziz et al. (2022) suggest synthesizing cellulose acetate or adding nanocellulose to make cellulose tougher, more flexible, and long-lasting than plastics. Cellulose acetate films exhibit tensile strengths of 60–1570 MPa, comparable to around 20 MPa in low-density polyethylene (Wang et al. 2021). Thereby, making cellulose-based materials to outperform petroleum-based ones. Consumer products and food packaging benefit from these lightweight, biodegradable, phthalate- and BPA-free plastic alternatives (Piergiovanni & Limbo 2016). Cellulose fabrics like rayon and lyocell are more breathable, absorbent, and comfortable than polyester or nylon (Ahmed & Akhtar 2017, Salleh et al. 2021). The Lyocell biodegrades within 6–8 weeks in soil, whereas polyester persists for decades or longer (Wang et al. 2021).

Packaging, textiles, and industrial uses compared to traditional plastics: In recent years, cellulose-based polymers have emerged as promising plastic substitutes for single-use goods, including bags, wraps, and containers.

Plastics protect against gases and moisture better than cellulose, although enhancing its water resistance and barrier qualities is difficult (Siró & Plackett 2010). Cellulose-based fibres like lyocell and viscose are replacing synthetics in textiles. Nanocellulose coatings can achieve oxygen permeability rates as low as 0.0006 to 0.009 cm³·µm/(m²·day·kPa) under dry conditions, which is significantly lower than that of conventional PET films, typically ranging from 1 to 3 cm³·µm/(m²·day·kPa). This superior barrier performance makes nanocellulose an attractive alternative for packaging applications requiring high oxygen resistance (Nair et al. 2014). In textiles, cellulose fibres achieve 90% biodegradation under aerobic conditions, compared to <5% for polyester and nylon (Egan & Salmon 2022). These materials offer higher moisture absorption, breathability, and biodegradability (Ahmed & Akhtar 2017). Bio-composites and the building sector are using cellulose-based goods more because they can replace petroleum-based materials like plastics and fibreglass. In the construction, aerospace, and automotive industries, cellulose nanofibers can strengthen and lighten bio-composites (Dufresne 2013, Hasan et al. 2020). Adding 5-10 wt% nanocellulose can enhance the tensile modulus of composites by 30-60%, while reducing weight, making cellulose-based composites attractive for automotive, aerospace, and construction applications (Hasan et al. 2020).

End-of-life Scenarios

Compostability, recyclability, and biodegradation pathways: Cellulose-based polymers have considerable benefits compared to petroleum-based plastics in terms of end-of-life outcomes (Fig. 2). Cellulose is naturally biodegradable, breaking down into organic molecules via microbial and enzymatic activities in natural settings, leaving no hazardous leftovers (Bisaria & Ghose 1981). Conversely, plastics can endure for decades, breaking down into microplastics that exacerbate environmental pollution (Thompson et al. 2009). The compostability of cellulose-based materials is a significant advantage. Numerous cellulose products, including paper-based packaging and cellulose films, are appropriate for composting in both industrial and domestic environments, decomposing into water, carbon dioxide, and biomass within months (Song et al. 2009). Cellulose-based packaging achieves approximately 90% mass loss within 180 days under simulated home composting conditions. Under industrial composting conditions, it meets EN 13432 standards by achieving >90% biodegradation within 12 weeks (Song et al. 2009). Cellulose acetate, a chemically modified cellulose derivative, exhibits significantly reduced biodegradability, especially when the degree of substitution is ≥ 2.5 (Yadav & Hakkarainen 2021).

To degrade, chemically modified cellulose products like cellulose acetate may need high temperatures and microbial activity (Tsuji 2013). The recycling of cellulose-based materials is achievable yet complex. Although paper and cardboard are widely recycled, other cellulose products, like textiles and composites, necessitate specialized recycling methods due to chemical additives and heterogeneous ingredients. Paper and cardboard recycling achieves approximately 70–90% fibre recovery over 4 to 6 recycling cycles, depending on the process conditions and fibre quality (Belle et al. 2024). Improving the recyclability of cellulose-based products is a vital research domain that underpins the feasibility of a circular economy.

Evaluating circular economy potential: Reuse, recovery, and recycling efficiency: The circular economy concept seeks to reduce waste by optimising material use via reuse, recycling, and recovery (MacArthur 2013). The biodegradability, recyclability, and renewability of cellulose-based materials render them very attractive in this context compared to plastic materials (Table 3). Cellulose elements in paper and cardboard can be recycled multiple times before becoming unusable, after which they can be composted or converted into energy (Thompson et al. 2009). Compared to virgin pulp production, paper and cardboard recycling reduces energy consumption by up to 60%, making it a more energy-efficient and environmentally sustainable option (Belle et al. 2024).

The extraction of nutrients from cellulose-based materials




Fig. 2: Life cycle assessment of plastics and cellulose-based materials.

through industrial composting or anaerobic digestion can enhance regenerative farming methods (Tjeerdma & Militz 2005). Furthermore, improvements in cellulose chemistry, particularly the synthesis of nanocellulose, facilitate the creation of high-performance products from recycled cellulose, thus diminishing dependence on virgin raw materials and prolonging product lifecycles (Dufresne 2017). Nanocellulose produced from recycled paper retains over 80% of the tensile strength and modulus compared to that from virgin pulp, supporting its suitability for high-value reuse in circular material applications (Kargupta et al. 2023).

TOXICITY AND MICROPLASTICS REDUCTION

Comparative Toxicology of Plastics and Cellulose-Based Materials

Chemical additives frequently utilised in plastics, particularly those sourced from petroleum, can improve attributes such as flexibility, durability, and transparency. Bisphenol A (BPA) and phthalates, commonly found in polycarbonate plastics and polyvinyl chloride (PVC), present considerable issues.

BPA acts as an endocrine disruptor, imitating oestrogen and disrupting hormonal activities in humans and wildlife, resulting in reproductive, developmental, and metabolic issues (Rubin 2011). Chemicals used to make plastic flexible, phthalates, can cause fertility problems, developmental disorders, and cancer (Meeker et al. 2009). Leachate studies show that plastics can release a wide range of hazardous compounds. For example, polycarbonate plastics can leach bisphenol A (BPA) in concentrations ranging from 0.036 to 1.1 mg/L under various conditions, while flexible PVC may release phthalates at levels up to 40% by weight, particularly during use involving contact with food or biological tissues (Hahladakis et al. 2023). Plastic leachates are released from various polymers such as PVC, PE, PP, PS, and PET through weathering, UV exposure, and microbial degradation (Omidoyin & Jho 2024). In marine environments, PBDE concentrations in plastics ranged from 0.3 to 9900 ng/g, while HBCD levels in expanded polystyrene fragments have been recorded as high as 14,500 µg/g (Hirai et al. 2011, Taniguchi et al. 2016, Jang et al. 2017). In freshwater systems like Taihu Lake, leachates include BPA (28–560 ng/L), nonylphenols

Table 3: Mechanical properties, applications, and challenges of cellulose-based and petroleum-based plastics.

Material	Tensile Strength	Water Resistance	Applications	Challenges	Proposed Solution	References
Cellulose Acetate	Moderate	Moderate	Packaging, film applications	Limited water resistance	Development of hydrophobic coatings	Moon et al. 2011, Klemm et al. 2005
Nanocellulose	High	Low	Bio-composites, medical devices	High production cost, scalability issues	Advancements in enzymatic processes, nanotechnology	Dufresne 2017
PLA (Bioplastic)	Moderate	High	Food packaging, medical use	Costly production, limited recyclability	Expansion of recycling infrastructure	Tsuji 2013
Polyethylene (Petroleum)	Very High	Very High	Industrial and consumer plastics	High microplastic pollution	None (non-biodegradable)	Siró & Plackett 2010
Cellulose Films	Low to Moderate	Low	Packaging, textiles	Low consumer awareness, high perceived cost	Public awareness campaigns on biodegradability	Verma et al. 2024
Polyvinyl Alcohol (PVA)	Low	Moderate	Food packaging, medical applications	Solubility in water limits applications	Blending with other biopolymers for strength	Sirviö et al. 2020
Polyhydroxyalkanoates (PHA)	High	Moderate	Biodegradable plastics, agricultural films	High production cost	Process optimization, policy support	Gewert et al. 2015
Starch-Based Bioplastics	Low	Low to Moderate	Single-use items, compostable bags	Weak mechanical properties	Blending with nanocellulose for strength	Garavito et al. 2024
Cellophane	Moderate	Low	Packaging, textile industry	Low durability in humid conditions	Surface modification for improved performance	Moon et al. 2011
Polycaprolactone (PCL)	High	High	Biomedical, packaging, compostable items	Limited scalability, high production costs	Scaling production, blending with other polymers	Dufresne 2017

(262–1443 ng/L), and OPFRs (~1097 ng/L) (Lu et al. 2011, Xiao-Ju et al. 2012, Yan et al. 2017). Soil contamination is also significant, with approximately 3905 tons of PAEs accumulated in Chinese soils from 1958 to 2019 (Bi et al. 2021) and up to 72% of DEHP from plastic products ending up in the soil (Wang et al. 2017). These data underscore the widespread occurrence of plastic leachate and its ecological significance across multiple environmental compartments. Conversely, cellulose-based products typically do not include these hazardous chemicals, as they are derived from natural, plant-based sources. Certain chemically modified cellulose derivatives, including cellulose acetate, may include additives; nonetheless, these are generally less toxic and pose lesser risks than synthetic plastics (Moon et al. 2011). Cellulose acetate films leached bisphenol A (BPA) at around 0.5 µg/L under standard use conditions. The leaching rate was significantly lower compared to conventional synthetic polymers. This level highlights the safer environmental profile of cellulose acetate in applications involving water contact (Islam et al. 2023). Cellulose derivatives employed in food packaging, textiles, and biomedical applications frequently obtain safety certifications from regulatory agencies such as the U.S. Food and Drug Administration (FDA) and the European Food Safety Authority (EFSA) (Klemm et al. 2005). Moreover, the biodegradability of cellulose materials mitigates accumulation in ecosystems, thereby diminishing long-term toxicological effects.

Microplastics are already pervasive in the environment and present considerable threats to both human and animal health. Plankton, fish, birds, and mammals in aquatic and terrestrial ecosystems eat microplastics. Microplastics can induce physical obstructions, reduced food consumption, and malnutrition in marine animals (Wright et al. 2013). Additionally, microplastics can absorb persistent organic pollutants (POPs), including PCBs and PAHs, from the environment. Microplastics release monomers and additives such as bisphenol A (BPA) and phthalates, which are known to leach from plastic matrices and disrupt endocrine function even at very low concentrations (Prata et al. 2020). These leachates induce oxidative stress, evidenced by increased reactive oxygen species and lipid peroxidation in zebrafish and mice exposed to polystyrene particles (Lu et al. 2016, Deng et al. 2017). Exposure to 5–20 µm PS particles in mice led to significant accumulation in the liver and kidney, causing metabolic disruption and oxidative damage (Deng et al. 2017). Immunotoxic effects include suppressed dendritic cell activation and cytokine imbalances, while mussels exposed to microplastics showed altered immune gene expression and reduced immune competence (Saravia et al. 2014). Additionally, endocrine-disrupting compounds leached from plastics have been linked to

hormonal imbalances and reproductive effects at low doses, highlighting the risk of chronic exposure through ingestion of up to 52,000 microplastic particles per person annually (Cox et al. 2019). Once in the food chain, these contaminants bioaccumulate and biomagnify (Rochman 2018). More individuals are afraid of eating microplastics from seafood, water, and air. Microplastics may cause oxidative stress, immune system disruption, inflammation, and other health issues, although researchers are still studying them (Prata et al. 2020). Microplastics can emit harmful chemicals like bisphenol A (BPA) and phthalates, and harm the ecosystem. Cellulose-based products do not degrade into hazardous microplastics. Since microorganisms and enzymes break down cellulose, eating glucose and other naturally occurring components is harmless. This feature considerably reduces bioaccumulation and health concerns (Klemm et al. 2005).

The Role of Cellulose-Based Materials in Mitigating Microplastics in Ecosystems

Cellulose-based polymers reduce microplastic contamination better than petroleum-based plastics. Cellulose, a natural polymer, biodegrades in soil, rivers, and seas without leaving toxic residues. However, synthetic polymer breakdown microplastics can endure generations (Andrady 2011). Switching to cellulose-based cutlery, packaging, and straws can reduce coastal microplastic pollution. Biodegradable and compostable cellulose-derived products reduce microplastic pollution in aquatic habitats. Marine microbes may easily break down these toxins into non-toxic organic molecules, as reported by Song et al. (2009).

Multiple studies have proven the prevalence of microplastics in aquatic ecosystems. Every year, 4.8–12.7 million metric tonnes of plastic debris enter the world's waters, contributing to microplastics (Jambeck et al. 2015). The Great Pacific Garbage Patch has dangerous quantities that are harming marine life (Eriksen et al. 2014). Briassoulis et al. (2019) compared cellulose-based film degradation in terrestrial and marine ecosystems to plastics. The study found that plastic films decay slowly, whereas cellulose films break down entirely within months. This suggests that employing cellulose polymers instead of petroleum plastics might dramatically shorten microplastics' ecosystem time. A second Mediterranean Sea case study examined cellulose-based marine debris reduction alternatives. Biodegradable cellulose-based fishing gear and packaging may reduce plastic pollution by 30% over ten years if waste management is successful (Bergmann et al. 2015). These findings show that cellulose-based products not only prevent microplastic generation but also reduce exposure to toxic leachates and endocrine disruptors associated with conventional plastics.

As such, cellulose-based alternatives contribute both to ecosystem health and to reduced chemical risks in the food chain.

REGULATORY AND ECONOMIC CONSIDERATIONS

Overview of International and National Regulations on Single-Use Plastics and Bioplastics

In recent years, some nations have established regulations to prevent plastic pollution, particularly single-use plastics. The EU's Single-Use Plastics Directive (2019) bans straws, cutlery, and polystyrene food containers. This law requires plastic bottles to be made from recycled material by 2025 and sets collection and recycling targets. As worries about

plastic pollution in landfills and waterways have increased, Kenya, Canada, and India have banned or severely restricted single-use plastics. The 2019 Basel Convention modifications ban the transboundary movement of plastic waste; thus, governments must acquire authorisation before exporting non-recyclable plastic waste (Ahmed 2019). These restrictions aim to halt the flow of plastic waste from affluent to poor nations, where a lack of waste treatment infrastructure degrades the environment. Bioplastics and other eco-friendly materials are being promoted in numerous countries to decrease plastic waste. The EU's Circular Economy Action Plan (2020) aims to increase biodegradable material consumption and improve the bio-based product market. National governments, including the US and Japan, have provided financial incentives and research initiatives to create

Table 4: Global regulations promoting biodegradable alternatives.

Year	Country/Region	Regulation/Initiative	Policy/Action	Reference
2002	Bangladesh	Plastic Bag Ban	First country to ban thin plastic bags due to drain blockage and flooding.	(UNEP 2018)
2015	USA	Microbead-Free Waters Act	Banning plastic microbeads in rinse-off cosmetics to prevent water contamination.	(NOAA 2015)
2016	Germany	Plastic Bag Tax	Introduced a voluntary agreement leading to ~60% drop in bag usage.	(DW 2016)
2017	Kenya	Plastic Bag Ban	Strictest penalties globally, including fines and jail terms for production/use.	(Griffin and Karasik 2022)
2018	Spain	Plastic Bag Charge	Mandatory charge for lightweight plastic bags, exemptions for very lightweight bags.	(European Commission 2019)
2019	European Union	Single-Use Plastics Directive	Ban on cutlery, straws, plates, targets for recycling and collection.	(European Commission 2019)
2020	France	Ban on Plastic Cutlery & Plates	Part of a wider anti-waste law banning disposable plastic items.	(Frontier Group 2023)
2021	China	Phased Plastic Ban	Gradual restrictions on plastic bags, straws, and delivery packaging.	(Library of Congress 2021)
2022	Colombia	Single-Use Plastics Prohibition	Law banning 14 single-use plastic products from 2022 to 2030.	(ADBioplastics 2024)
2022	India	Single-Use Plastic Ban	Ban on manufacture, import, stocking, distribution, sale and use of listed plastic items.	(MoEFCC 2023)
2023	Canada	Single-Use Plastics Ban	Prohibits the sale and manufacture of plastic checkout bags, cutlery, straws, and other items.	(Government of Canada 2023)
2025	European Union	Packaging and Packaging Waste Regulation (PPWR)	Requires all packaging to be recyclable or reusable by 2030, mandates compostability criteria.	(European Commission 2025)
2023	France	Plastic Bottle Sales Reduction Target	Goal to cut single-use plastic bottle sales by 50% by 2030.	(Le Monde 2023)
2021	New Zealand	Single-Use Plastics Ban	Banned single-use plastic items such as cotton buds, drink stirrers, and fruit labels.	(Crux 2021)
2022	Nigeria	Single-Use Plastics Ban	Scheduled to ban single-use plastics, including plastic bags and straws, to combat environmental pollution.	(Sustainable Plastics 2024)
2024	United Arab Emirates	Single-Use Plastics Ban	Plans to ban single-use plastic food containers and cutlery to reduce plastic waste. The country aims to achieve zero plastic waste by 2030 as part of its larger environmental vision.	(UAE Stories 2024)

bioplastics and cellulose-based alternatives to conventional plastics (OECD 2014). Bioplastics are growing in popularity, yet cellulose-based products are still behind petroleum-based polymers. Government subsidies, tax cuts, and research grants are needed to promote cellulose-based alternatives. The European Bio-based Industries Joint Undertaking funds research and development of bio-based materials, primarily cellulose-derived polymers (Bio-based Industries Joint Undertaking 2022). Additionally, certain nations' public procurement regulations encourage biodegradable and compostable materials in public services and packaging, which expands these markets. The USDA BioPreferred Program in North America encourages bio-based goods, notably cellulose-based ones. This campaign encourages bio-based purchases and use through government procurement laws. After many public governments banned single-use plastics and required biodegradable or compostable alternatives, cellulose-based goods are becoming the standard. Table 4 outlines a chronological progression of key global regulatory actions targeting plastic pollution by promoting biodegradable alternatives.

Many developing nations face significant regulatory and implementation challenges. The global initiative to mitigate plastic pollution is affected by weak enforcement of bans on plastic materials, insufficient waste collection infrastructure, and ambiguous regulations concerning biodegradable plastics (Islam et al 2024). Capacities for enforcement and compliance monitoring do not exist in most countries that officially restrict single-use plastics (Islam et al. 2024); hence, these countries continue to consume plastic. Developing regions face an additional challenge of limited administrative capacity paired with fragmented governance structures. Inadequate infrastructure for managing waste stagnates the processes involved in properly collecting and sorting plastic waste needed for recycling. Investment-related incentives are dampened due to logistical challenges and market uncertainty facing recycling systems (OECD 2018, Gerassimidou et al. 2022). Furthermore, undefined and unenforceable rules concerning biodegradable plastics allow for the continued existence of harmful products meant to be regulated in nature without being entirely removed from ecosystems. Policy changes, infrastructure development alongside coordinated multilateral agreements, and defined international guidelines would help fill the noted gaps (Islam et al. 2024).

Economic Viability of Cellulose-Based Materials

Cellulose-based polymers are uneconomical because they cost more to make than petroleum-based plastics. Costs depend on the delicate procedures involved in collecting and processing cellulose from premium sources like wood

pulp or agricultural byproducts (Shen et al. 2010). However, economies of scale, well-established production techniques, and decreased raw material costs due to natural gas and crude oil abundance favour traditional plastics. Cellulose-based products must be mass-produced to be profitable. Improved production should lower per-unit costs. Dufresne (2017) suggests that nanocellulose production might save costs by improving extraction and refining efficiency. Moreover, escalating petroleum prices and heightened regulatory restrictions on plastic use may improve the economic viability of cellulose-based alternatives, particularly as the external environmental and social costs of plastic pollution are increasingly incorporated into market pricing.

Nonetheless, augmenting cellulose manufacturing entails numerous technical and economic obstacles. Industrial-scale operations necessitate significant investments in research and infrastructure, especially for sophisticated processing methods such as enzymatic hydrolysis and nanocellulose extraction (Klemm et al. 2005). Furthermore, the shift from small-scale niche production to mass manufacture must tackle technological challenges with product uniformity, performance, and integration with current manufacturing processes. For developing nations, economic barriers are particularly acute. High capital costs, limited technical expertise, and inadequate financial incentives constrain local production of cellulose-based materials.

Market adoption is also contingent upon consumer acceptance and willingness to invest in sustainable options. There is a growing consumer preference for environmentally friendly products in select markets, which could potentially boost demand for cellulose-based materials. Nonetheless, broad adoption will require further cost reductions and improvements in product performance to ensure competitiveness with the durability and functionality of conventional plastics in applications such as packaging and consumer goods (Siró & Plackett 2010).

Barriers to Widespread Implementation

Several technological and economic challenges impede the widespread adoption of cellulose-based materials (Li et al. 2024, Wang et al. 2024). Enhancing the properties of cellulose-derived products—such as moisture resistance, flexibility, and strength—requires continuous innovation (Zhao et al. 2021). For instance, cellulose films and packaging often lack the barrier properties inherent in petroleum-based plastics, rendering them less suitable for specific food packaging applications (Wang et al. 2018). Furthermore, modifying cellulose to improve its properties, such as conversion to cellulose acetate or nanocellulose, can increase costs, undermining its competitive edge. Economic challenges include the substantial initial

investment required for new manufacturing processes and the limited availability of sustainably sourced raw materials on a large scale. While cellulose is abundant, sustainable sourcing and industrial-scale processing can incur significant expenses (Wang et al. 2024). Additionally, cellulose-based materials must compete with established petroleum-based plastics, which benefit from extensive infrastructure investments and economies of scale.

Consumer behaviour also poses a challenge, as many consumers are unaware of the environmental benefits of cellulose-based alternatives or may hesitate to switch due to concerns about performance and cost (Filho et al. 2022). Addressing these behavioural barriers necessitates educational initiatives and improvements in the affordability and functionality of cellulose-based products (Filho et al. 2022). A critical barrier to the widespread adoption of cellulose-based materials is the insufficient infrastructure for recycling and composting (Parveen et al. 2024). While cellulose is biodegradable and compostable, numerous chemically modified or composite cellulose products necessitate certain conditions for efficient composting or recycling. Cellulose acetate, frequently utilized in packaging, often fails to disintegrate in home composting settings and generally requires industrial composting facilities for thorough degradation (Song et al. 2009). The current infrastructure, which is predominantly designed for conventional plastics, limits the recycling capability for cellulose-based products (Parveen et al. 2024). Enhancing this recycling infrastructure to include biodegradable and cellulose-based items will necessitate substantial expenditures in sorting technologies, industrial composting facilities, and consumer education. In developing nations, these infrastructure deficits are even more pronounced. Most waste management systems focus on landfill and informal recycling, with minimal capacity for industrial composting or specialised cellulose recycling. Unless these infrastructural inadequacies are rectified, the prospective environmental advantages of cellulose-based materials may remain unfulfilled.

FUTURE DIRECTIONS AND INNOVATION OPPORTUNITIES

Technological Innovations

Recent advances have made cellulose-based polymers a viable alternative to plastics. Researchers have transformed cellulose's nanoscale structure to boost its mechanical strength and flexibility (Ray et al. 2021). This is shown in nanocellulose, which contains cellulose nanocrystals -CNCs and cellulose nanofibrils -CNFs (Du et al. 2019, Dufresne 2019). Its high strength-to-weight ratio makes it ideal for packaging, coatings, and composites, and its mechanical

qualities rival petroleum-based polymers (Dufresne 2017). Besides mechanical qualities, research on cellulose-based material water resistance has garnered a lot of interest. Due to its hydrophilic nature and rapid moisture absorption, natural cellulose is restricted in moisture-sensitive packaging. Acetylation and hydrophobic coatings boost the performance of water resistance, packaging, and food contact (Klemm et al. 2005). Cellulose and biodegradable polymers like polylactic acid have been combined to generate composite materials with increased moisture resistance and durability.

Modern cellulose processing uses ionic liquids and deep eutectic solvents to dissolve cellulose (Taokaew & Kriangkrai 2022). These safe solvents degrade cellulose without harsh chemicals, reducing its environmental impact (Sirviö et al. 2020). Enzymatic processing optimizes cellulose materials to reduce emissions and energy use compared to kraft pulping (Isikgor & Becer 2015).

Cellulose three-dimensional printing is novel. Cellulose-based additive manufacturing can mass-produce biodegradable, custom-shaped goods for building, medicine, and other industries (Chen et al. 2020). Nanocellulose-based 3D printing inks are expanding the use of cellulose materials in eco-friendly, high-performance manufacturing (Chauhan et al. 2024, Kim et al. 2024). Fig. 3 presents a SWOT analysis of cellulose-based materials, highlighting their biodegradability and renewable origin as strengths while identifying scalability and competition from conventional plastics as key challenges.

Policy and Industry Integration

To advance cellulose-based products, policymakers and industry stakeholders must work together. Restricting single-

<p>STRENGTHS</p> <ul style="list-style-type: none"> • Biodegradable • Low toxicity • Renewable origin • Carbon sequestration • Good mechanical properties 	<p>WEAKNESSES</p> <ul style="list-style-type: none"> • Higher cost • Water sensitivity • Limited barrier properties • Processing limitations • Shorter shelf life
<p>OPPORTUNITIES</p> <ul style="list-style-type: none"> • Nanocellulose applications • Functional coatings • Policy support • Waste valorization • Blending with other biopolymers 	<p>THREATS</p> <ul style="list-style-type: none"> • Scalability • Competition from conventional plastics • Lack of consumer awareness • Performance gaps • Supply chain constraints

Fig. 3: SWOT Analysis of Cellulose-Based Materials as Alternatives to Conventional Plastics.

use plastics can accelerate the transition to biodegradable materials such as cellulose (OECD 2018). Comprehensive cellulose recycling and composting rules are needed to balance end-of-life management with environmental aims (Sikorska et al. 2021, Gadaleta et al. 2023). Collaboration between industry and research institutions is necessary for innovation and production scalability. Research and development are needed to improve the performance of cellulose-based materials and decrease their cost to compete with petroleum-based polymers. The packaging, textile, and consumer products sectors want sustainable solutions (Siró & Plackett 2010). Companies in these areas should integrate cellulose-based goods into their supply chains. Public-private partnerships (PPPs) can help innovate cellulose-based products. This type of partnership accelerates technology development and commercialization by pooling expertise, assets, and finance. The EU Bio-based Industries Joint Undertaking (BBI JU) funds cellulose product development projects. Industries, academic institutions, and governments should collaborate on this endeavour to tackle commercial and technical problems. PPPs may also align industry practices with regulations by boosting green production and waste management. Government incentives or co-investments may assist cellulose-based material producers in developing and embracing new technologies. PPPs can speed cellulose-based product development and deployment by fostering cross-sector collaboration.

Research Gaps and Prospective Investigations

Cellulose-based materials have advanced, but further study is needed to enhance their environmental advantages. Comprehensive lifecycle assessments (LCAs) are used to examine the environmental implications of cellulose-based products from extraction to disposal (Foroughi et al. 2021). Though renewable, cellulose extraction and processing have different environmental implications depending on feedstock and manufacturing procedures (Shen et al. 2010). More research is needed to improve these processes while reducing energy, water, and pollutants. The biodegradation of cellulose acetate and other chemically modified cellulose derivatives is crucial to study. Undamaged cellulose is biodegradable, although chemical changes may hinder it. Future research should aim to make modified cellulose materials biodegradable so they can break down in soil and water without leaving a deposit (Song et al. 2009). Cellulose-derived items in the bio-circular economy are a promising new research area. The bio-circular economy emphasizes waste reduction, renewable resources, and recycling (MacArthur 2013). Cellulose fits this paradigm since it's renewable, biodegradable, and recyclable. Effectively integrating cellulose materials into circular supply networks requires additional research. Research should focus

on recycling composites and chemically modified cellulose, which are unsuitable for current procedures. New cellulose uses, like bio-composites and eco-friendly packaging, can boost bio-circular economy performance. According to Tjeerdsma & Militz (2005), governments and companies must collaborate to provide composting, recycling, and reuse infrastructure for cellulose-based goods to contribute to a sustainable economy.

CONCLUSIONS

Cellulose-derived materials offer a promising pathway to mitigate plastic pollution due to their biodegradability, compostability, and lower greenhouse gas emissions compared to petroleum-based plastics. They naturally decompose in terrestrial and marine environments, avoiding the long-term persistence and toxic effects associated with microplastics. Despite these advantages, technical and economic barriers remain. Unmodified cellulose lacks sufficient water resistance and mechanical strength, while chemical modifications such as cellulose acetate and nanocellulose introduce additional costs and processing challenges. Scaling production and improving material performance are essential to enhance market competitiveness. Achieving a broader transition to cellulose-based materials requires coordinated action. Industry should invest in R&D to develop cost-effective and environmentally friendly production processes. Governments can support this shift through targeted legislation, tax incentives, and investment in recycling and composting infrastructure. Public procurement policies and consumer education will further drive demand and market growth. Future efforts must focus on overcoming affordability, scalability, and end-of-life management challenges. Advancing cellulose-based solutions through innovation, public-private collaboration, and informed policy will contribute significantly to a sustainable and circular economy. In addressing the global plastic crisis, cellulose-based alternatives represent a critical step towards a cleaner and more resilient future.

REFERENCES

- ADBioplastics, 2024. Legislation on Single-Use Plastics and Products in Colombia: Keys, Trends and Opportunities. Retrieved April 24, 2025, from <https://adbioplastics.com/en/legislation-on-single-use-plastics-and-products-in-colombia-keys-trends-and-opportunities/>
- Ahmed, I., 2019. The Basel Convention on the control of transboundary movements of hazardous wastes and their disposal: A legal misfit in global ship recycling jurisprudence. *Washington International Law Journal*, 29(2), pp.411–450.
- Ahmed, S. and Akhtar, K.S., 2017. Textile raw materials. Higher Education Commission Pakistan, Islamabad, pp.420.
- Andrady, A.L. and Neal, M.A., 2009. Applications and societal benefits of plastics. *Philosophical Transactions of the Royal Society B: Biological Sciences*, 364(1526), pp.1977–1984.

- Andrady, A.L., 2011. Microplastics in the marine environment. *Marine Pollution Bulletin*, 62(8), pp.1596–1605.
- Awuchi, C.G. and Awuchi, C.G., 2019. Impacts of plastic pollution on the sustainability of seafood value chain and human health. *International Journal of Advanced Academic Research*, 5(11), pp.46–138.
- Aziz, T., Farid, A., Haq, F., Kiran, M., Ullah, A., Zhang, K., Li, C., Ghazanfar, S., Sun, H., Ullah, R. and Ali, A., 2022. A review on the modification of cellulose and its applications. *Polymers*, 14(15), pp.3206–3225.
- Azwa, Z.N., Yousif, B.F., Manalo, A.C. and Karunasena, W., 2013. A review on the degradability of polymeric composites based on natural fibres. *Materials and Design*, 47, pp.424–442.
- Badar, S. and Farooqi, I.H., 2012. Pulp and paper industry—manufacturing process, wastewater generation and treatment. In: *Environmental Protection Strategies for Sustainable Development*. Academic Press, London, pp.397–436.
- Belle, J., Hirtz, D. and Sänglerlaub, S., 2024. Expert survey on the impact of cardboard and paper recycling processes, fiber-based composites and regulations, and their significance for the circular economy and the sustainability of the German paper industry. *Sustainability*, 16(15), pp.6610–6630.
- Bergmann, M., Gutow, L. and Klages, M., 2015. Marine anthropogenic litter. Springer Nature, Berlin, pp.447.
- Bi, M., Liu, W., Luan, X., Li, M., Liu, M., Liu, W. and Cui, Z., 2021. Production, use and fate of phthalic acid esters for polyvinyl chloride products in China. *Environmental Science and Technology*, 55(20), pp.13980–13989.
- Bisaria, V.S. and Ghose, T.K., 1981. Biodegradation of cellulosic materials: Substrates, microorganisms, enzymes and products. *Enzyme and Microbial Technology*, 3(2), pp.90–104.
- Briassoulis, D., Pikasi, A., Briassoulis, C. and Mistriotis, A., 2019. Disintegration behaviour of bio-based plastics in coastal zone marine environments: A field experiment under natural conditions. *Science of the Total Environment*, 688, pp.208–223.
- Carvalho, D., Ferreira, N., França, B., Marques, R., Silva, M., Silva, S., Silva, E., Macário, D., Barroso, L., Silva, C.J. and Oliveira, C., 2024. Advancing sustainability in the automotive industry: Bioprepreps and fully bio-based composites. *Composites Part C: Open Access*, 6(1), pp.100459–100470.
- Cashore, B., Gale, F., Meidinger, E. and Newsom, D., 2006. Forest certification in developing and transitioning countries: Part of a sustainable future? *Environment: Science and Policy for Sustainable Development*, 48(9), pp.6–25.
- Chauhan, C., Rani, V., Kumar, M. and Motla, R., 2024. Utilising biomass-derived composites in 3D printing to develop eco-friendly environment. In: *Valorization of Biomass Wastes for Environmental Sustainability: Green Practices for the Rural Circular Economy*. Springer Nature Switzerland, Cham, pp.153–170.
- Chen, W., Yu, H., Lee, S.Y., Wei, T., Li, J. and Fan, Z., 2018. Nanocellulose: A promising nanomaterial for advanced electrochemical energy storage. *Chemical Society Reviews*, 47(8), pp.2837–2872.
- Condé, T.M., Tonini, H., Higuchi, N., Higuchi, F.G., Lima, A.J.N., Barbosa, R.I., dos Santos Pereira, T. and Haas, M.A., 2022. Effects of sustainable forest management on tree diversity, timber volumes and carbon stocks in an ecotone forest in the northern Brazilian Amazon. *Land Use Policy*, 119, pp.106145–106160.
- Cox, K.D., Covernton, G.A., Davies, H.L., Dower, J.F., Juanes, F. and Dudas, S.E., 2019. Human consumption of microplastics. *Environmental Science and Technology*, 53(12), pp.7068–7074.
- Crux, 2021. More Single-Use Plastics Banned by 2025. Retrieved April 24, 2025, from <https://crux.org.nz/national-news/more-single-use-plastics-banned-by-2025>
- Datta, R., 2024. Enzymatic degradation of cellulose in soil: A review. *Heliyon*, 10(2), pp.e24022–e24040.
- Deng, Y., Zhang, Y., Lemos, B. and Ren, H., 2017. Tissue accumulation of microplastics in mice and biomarker responses suggest widespread health risks of exposure. *Scientific Reports*, 7(1), pp.46687–46700.
- Du, H., Liu, W., Zhang, M., Si, C., Zhang, X. and Li, B., 2019. Cellulose nanocrystals and cellulose nanofibrils based hydrogels for biomedical applications. *Carbohydrate Polymers*, 209, pp.130–144.
- Dufresne, A., 2013. Nanocellulose: A new ageless bionanomaterial. *Materials Today*, 16(6), pp.220–227.
- Dufresne, A., 2017. Nanocellulose: From Nature to High Performance Tailored Materials. Walter de Gruyter GmbH & Co. KG, Berlin, pp.460.
- Dufresne, A., 2019. Nanocellulose processing properties and potential applications. *Current Forestry Reports*, 5(2), pp.76–89.
- DW, 2016. German Strikes Retail Deal on Plastic Bags. Retrieved April 24, 2025, from <https://www.dw.com/en/german-government-signs-deal-to-reduce-plastic-bag-use/a-19215270>
- Egan, J. and Salmon, S., 2022. Strategies and progress in synthetic textile fiber biodegradability. *SN Applied Sciences*, 4(1), pp.1–36.
- Erdal, N.B. and Hakkarainen, M., 2022. Degradation of cellulose derivatives in laboratory, man-made and natural environments. *Biomacromolecules*, 23(7), pp.2713–2729.
- Eriksen, M., Lebreton, L.C., Carson, H.S., Thiel, M., Moore, C.J., Borro, J.C., Galgani, F., Ryan, P.G. and Reisser, J., 2014. Plastic pollution in the world's oceans: More than 5 trillion plastic pieces weighing over 250,000 tons afloat at sea. *PLoS ONE*, 9(12), pp.e111913–e111930.
- European Commission Action Plan (CEAP), 2020. *For a Cleaner and More Competitive Europe*. European Commission, Brussels, pp.28.
- European Commission, 2019. Single-Use Plastics. Retrieved April 24, 2025, from https://environment.ec.europa.eu/topics/plastics/single-use-plastics_en
- European Commission, 2019. The Plastic Bags Directive. Retrieved April 24, 2025, from https://environment.ec.europa.eu/topics/plastics/plastic-bags_en
- European Commission, 2025. Packaging Waste. Retrieved April 24, 2025, from https://environment.ec.europa.eu/topics/waste-and-recycling/packaging-waste_en
- Felgueiras, C., Azoia, N.G., Gonçalves, C., Gama, M. and Dourado, F., 2021. Trends on the cellulose-based textiles: Raw materials and technologies. *Frontiers in Bioengineering and Biotechnology*, 9(1), pp.608826–608840.
- Filho, W.L., Barbir, J., Abubakar, I.R., Paço, A., Stasiskiene, Z., Hornbogen, M., Fendt, M.T.C., Voronova, V. and Klöga, M., 2022. Consumer attitudes and concerns with bioplastics use: An international study. *PLoS ONE*, 17(4), pp.e0266918–e0266935.
- Forfora, N., Azuaje, I., Vivas, K.A., Vera, R.E., Brito, A., Venditti, R., Kelley, S., Tu, Q., Woodley, A. and Gonzalez, R., 2024. Evaluating biomass sustainability: Why belowground carbon sequestration matters. *Journal of Cleaner Production*, 439(1), pp.140677–140690.
- Foroughi, F., Rezvani Ghomi, E., Morshedi Dehaghi, F., Borayek, R. and Ramakrishna, S., 2021. A review on the life cycle assessment of cellulose: From properties to the potential of making it a low carbon material. *Materials*, 14(4), pp.714–730.
- Frontier Group, 2023. How France's Anti-Waste Law Targets Plastic Waste at Its Source. Retrieved April 24, 2025, from <https://frontiergroup.org/articles/how-frances-anti-waste-law-targets-plastic-waste-at-its-source/>
- Gadaleta, G., Ferrara, C., De Gisi, S., Notarnicola, M. and De Feo, G., 2023. Life cycle assessment of end-of-life options for cellulose-based bioplastics when introduced into a municipal solid waste management system. *Science of the Total Environment*, 871(1), pp.161958–161970.
- Gall, S.C. and Thompson, R.C., 2015. The impact of debris on marine life. *Marine Pollution Bulletin*, 92(1–2), pp.170–179.
- Garavito, J., Peña-Venegas, C.P. and Castellanos, D.A., 2024. Production of starch-based flexible food packaging in developing countries: Analysis of the processes, challenges and requirements. *Foods*, 13(24), pp.4096–4110.

- Gerassimidou, S., Lovat, E., Ebner, N., You, W., Giakoumis, T., Martin, O.V. and Iacovidou, E., 2022. Unpacking the complexity of the UK plastic packaging value chain: A stakeholder perspective. *Sustainable Production and Consumption*, 30, pp.657–673.
- Gewert, B., Plassmann, M.M. and MacLeod, M., 2015. Pathways for degradation of plastic polymers floating in the marine environment. *Environmental Science: Processes and Impacts*, 17(9), pp.1513–1521.
- Geyer, R., Jambeck, J.R. and Law, K.L., 2017. Production, use and fate of all plastics ever made. *Science Advances*, 3(7), pp.e1700782–e1700795.
- Ghosh, S., Sinha, J.K., Ghosh, S., Vashisth, K., Han, S. and Bhaskar, R., 2023. Microplastics as an emerging threat to the global environment and human health. *Sustainability*, 15(14), pp.10821–10840.
- Giacovelli, C., 2018. Single-Use Plastics: A Roadmap for Sustainability. United Nations Environment Programme, Nairobi, pp.110.
- Gilbert, M., 2017. Plastics materials: Introduction and historical development. In: Brydson's Plastics Materials. Butterworth-Heinemann, Oxford, pp.1–18.
- Giordanengo, G., 2024. Development of Innovative Materials and Processes for Cellulose-Based Food Packaging in a Circular Economy Perspective. Technical Report, European Materials Institute, Milan, pp.95.
- Godswill, A.C. and Godspel, A.C., 2019. Physiological effects of plastic wastes on the endocrine system (bisphenol A, phthalates, bisphenol S, PBDEs, TBBPA). *International Journal of Bioinformatics and Computational Biology*, 4(2), pp.11–29.
- Government of Canada, 2023. Single-Use Plastics Prohibition Regulations – Overview. Retrieved April 24, 2025, from <https://www.canada.ca/en/environment-climate-change/services/managing-reducing-waste/reduce-plastic-waste/single-use-plastic-overview.html>
- Greene, J., Skolnik, C.L. and Merritt, M.W., 2022. How medicine becomes trash: Disposability in health care. *The Lancet*, 400(10360), pp.1298–1299.
- Griffin, M. and Karasik, R., 2022. Plastic Pollution Policy Country Profile: Kenya. Nicholas Institute for Energy, Environment & Sustainability, Duke University, Durham, pp.42.
- Groh, K.J., Backhaus, T., Carney-Almroth, B., Geueke, B., Inostroza, P.A., Lennquist, A., Leslie, H.A., Maffini, M., Slunge, D., Trasande, L. and Warhurst, A.M., 2019. Overview of known plastic packaging-associated chemicals and their hazards. *Science of the Total Environment*, 651(1), pp.3253–3268.
- Grzybek, P., Dudek, G. and van der Bruggen, B., 2024. Cellulose-based films and membranes: A comprehensive review on preparation and applications. *Chemical Engineering Journal*, 472(1), pp.153500–153520.
- Gupta, M.K. and Singhal, V., 2022. Review on materials for making lightweight vehicles. *Materials Today: Proceedings*, 56(1), pp.868–872.
- Habibi, Y., Lucia, L.A. and Rojas, O.J., 2010. Cellulose nanocrystals: Chemistry, self-assembly and applications. *Chemical Reviews*, 110(6), pp.3479–3500.
- Hahladakis, J.N., Iacovidou, E. and Gerassimidou, S., 2023. An overview of the occurrence, fate and human risks of bisphenol-A present in plastic materials, components and products. *Integrated Environmental Assessment and Management*, 19(1), pp.45–62.
- Hasan, K.F., Horváth, P.G. and Alpár, T., 2020. Potential natural fibre polymeric nanobiocomposites: A review. *Polymers*, 12(5), pp.1072–1090.
- Hirai, H., Takada, H., Ogata, Y., Yamashita, R., Mizukawa, K., Saha, M., Kwan, C., Moore, C., Gray, H. and Laursen, D., 2011. Organic micropollutants in marine plastic debris from the open ocean and remote and urban beaches. *Marine Pollution Bulletin*, 62(8), pp.1683–1692.
- Hopewell, J., Dvorak, R. and Kosior, E., 2009. Plastics recycling: Challenges and opportunities. *Philosophical Transactions of the Royal Society B: Biological Sciences*, 364(1526), pp.2115–2126.
- Isikgor, F.H. and Becer, C.R., 2015. Lignocellulosic biomass: A sustainable platform for the production of bio-based chemicals and polymers. *Polymer Chemistry*, 6(25), pp.4497–4559.
- Islam, M.D., Uddin, F.J., Rashid, T.U. and Shahruzzaman, M., 2023. Cellulose acetate-based membrane for wastewater treatment: A state-of-the-art review. *Materials Advances*, 4(18), pp.4054–4102.
- Islam, M.S., Lee, Z., Shaleh, A. and Soo, H.S., 2024. The United Nations Environment Assembly resolution to end plastic pollution: Challenges to effective policy interventions. *Environment, Development and Sustainability*, 26(5), pp.10927–10944.
- Jambeck, J.R., Geyer, R., Wilcox, C., Siegler, T.R., Perryman, M., Andrady, A., Narayan, R. and Law, K.L., 2015. Plastic waste inputs from land into the ocean. *Science*, 347(6223), pp.768–771.
- Jang, M., Shim, W.J., Han, G.M., Rani, M., Song, Y.K. and Hong, S.H., 2017. Widespread detection of a brominated flame retardant in expanded polystyrene marine debris and microplastics from the Asia-Pacific region. *Environmental Pollution*, 231(1), pp.785–794.
- Jing, L., Shi, T., Chang, Y., Meng, X., He, S., Xu, H., Yang, S. and Liu, J., 2024. Cellulose-based materials in environmental protection: A scientometric and visual analysis review. *Science of the Total Environment*, 912(1), pp.172576–172590.
- Joshi, S.V., Drzal, L.T., Mohanty, A.K. and Arora, S., 2015. Are natural fibre composites environmentally superior to glass fibre reinforced composites? *Composites Part A: Applied Science and Manufacturing*, 35(3), pp.371–376.
- Karak, N. (ed.), 2024. *Advances in Biocomposites and Their Applications*. Elsevier, Oxford, pp.612.
- Kargupta, W., Stevenson, T., Sharman, S., Tanner, J. and Batchelor, W., 2023. Sustainable production of nanocellulose: Technoeconomic assessment, energy savings and scalability. *Journal of Cleaner Production*, 425(1), pp.138748–138760.
- Khan, M.R., Wasim, M., Farooq, A., Naeem, M.A., Mushtaq, M., Liu, J., Chen, C. and Wei, Q., 2024. A review study on derivation of nanocellulose to its functional properties and applications in drug delivery systems, food packaging and biosensing devices. *Polymer Bulletin*, 81(11), pp.9519–9568.
- Kim, H., Dutta, S.D., Randhawa, A., Patil, T.V., Ganguly, K., Acharya, R., Lee, J., Park, H. and Lim, K.T., 2024. Recent advances and biomedical applications of 3D printed nanocellulose-based adhesive hydrogels: A review. *International Journal of Biological Macromolecules*, 254(1), pp.130732–130750.
- Kim, T., Bamford, J., Gracida-Alvarez, U.R. and Benavides, P.T., 2022. Life cycle greenhouse gas emissions and water and fossil-fuel consumption for polyethylene furanoate and its coproducts from wheat straw. *ACS Sustainable Chemistry & Engineering*, 10(8), pp.2830–2843.
- Klemm, D., Heublein, B., Fink, H.P. and Bohn, A., 2005. Cellulose: A fascinating biopolymer and sustainable raw material. *Angewandte Chemie International Edition*, 44(22), pp.3358–3393.
- Latha, A., Arivukarasi, M.C., Keerthana, C.M., Subashri, R. and Vishnu Priya, V., 2018. Paper and pulp industry manufacturing and treatment processes: A review. *International Journal of Engineering*, 6(2), pp.177–189.
- Lebreton, L.C.M., van der Zwet, J., Damsteeg, J.W., Slat, B., Andrady, A. and Reisser, J., 2017. River plastic emissions to the world's oceans. *Nature Communications*, 8(1), pp.15611–15620.
- Li, X., Wan, C., Tao, T., Chai, H., Huang, Q., Chai, Y. and Wu, Y., 2024. An overview of the development status and applications of cellulose-based functional materials. *Cellulose*, 31(1), pp.61–99.
- Library of Congress, 2021. China: Single-Use Plastic Straw and Bag Ban Takes Effect. Retrieved April 24, 2025, from <https://www.loc.gov/item/global-legal-monitor/2021-03-23/china-single-use-plastic-straw-and-bag-ban-takes-effect/>
- Lu, G., Yan, Z., Wang, Y. and Chen, W., 2011. Assessment of estrogenic contamination and biological effects in Lake Taihu. *Ecotoxicology*, 20(5), pp.974–981.

- Lu, Y., Zhang, Y., Deng, Y., Jiang, W., Zhao, Y., Geng, J., Ding, L. and Ren, H., 2016. Uptake and accumulation of polystyrene microplastics in zebrafish (*Danio rerio*) and toxic effects in the liver. *Environmental Science & Technology*, 50(7), pp.4064–4073.
- Lusher, A.L., McHugh, M. and Thompson, R.C., 2013. Occurrence of microplastics in the gastrointestinal tract of pelagic and demersal fish from the English Channel. *Marine Pollution Bulletin*, 67(1–2), pp.94–99.
- Lynd, L.R., Weimer, P.J., van Zyl, W.H. and Pretorius, I.S., 2002. Microbial cellulose utilisation: Fundamentals and biotechnology. *Microbiology and Molecular Biology Reviews*, 66(3), pp.506–577.
- MacArthur, E., 2013. Towards the circular economy. *Journal of Industrial Ecology*, 2(1), pp.23–44.
- Maraveas, C., 2020a. Environmental sustainability of plastic in agriculture. *Agriculture*, 10(8), pp.310–325.
- Maraveas, C., 2020b. Production of sustainable and biodegradable polymers from agricultural waste. *Polymers*, 12(5), pp.1127–1140.
- Meeker, J.D., Sathyanarayana, S. and Swan, S.H., 2009. Phthalates and other additives in plastics: Human exposure and associated health outcomes. *Philosophical Transactions of the Royal Society B: Biological Sciences*, 364(1526), pp.2097–2113.
- Ministry of Environment, Forest and Climate Change (MoEFCC), 2023. *Single Use Plastic Items Prohibited with Effect from 1st July 2022*. Retrieved April 24, 2025, from <https://pib.gov.in/PressReleaseIframePage.aspx?PRID=1942104>
- Moon, R.J., Martini, A., Nairn, J., Simonsen, J. and Youngblood, J., 2011. Cellulose nanomaterials review: Structure, properties and nanocomposites. *Chemical Society Reviews*, 40(7), pp.3941–3994.
- Mujtaba, M., Fraceto, L.F., Fazeli, M., Mukherjee, S., Savassa, S.M., de Medeiros, G.A., Santo Pereira, A.D.E., Mancini, S.D., Lipponen, J. and Vilaplana, F., 2023. Lignocellulosic biomass for agricultural waste to the circular economy: A review with focus on biofuels, biocomposites and bioplastics. *Journal of Cleaner Production*, 402(1), pp.136815–136830.
- Nair, S.S., Zhu, J.Y., Deng, Y. and Ragauskas, A.J., 2014. High performance green barriers based on nanocellulose. *Sustainable Chemical Processes*, 2(1), pp.1–7.
- National Oceanic and Atmospheric Administration (NOAA), 2015. *The President Signs a National Microbead Ban*. Retrieved April 24, 2025, from <https://blog.marinedebris.noaa.gov/president-signs-national-microbead-ban>
- Obuzor, G.U. and Onyedikachi, U.B., 2023. Chemical leaching into food and the environment poses health hazards. In: A. Editor and B. Editor (eds.) *Modernity in Health and Disease Diagnosis: The Account from STEM Women*. Springer Nature Switzerland, Cham, pp.129–148.
- Omidoyin, K.C. and Jho, E.H., 2024. Environmental occurrence and ecotoxicological risks of plastic leachates in aquatic and terrestrial environments. *Science of the Total Environment*, 938(1), pp.176728–176745.
- Organisation for Economic Co-operation and Development (OECD), 2014. *The State of Play on Extended Producer Responsibility (EPR): Opportunities and Challenges*. Retrieved June 29, 2025, from <https://docslib.org/doc/10687134/the-state-of-play-on-extended-producer-responsibility-epr-opportunities-and-challenges>
- Organisation for Economic Co-operation and Development (OECD), 2018. *Improving Plastics Management: Trends, Policy Responses, and the Role of International Co-operation and Trade*. Environmental Policy Papers, 12, pp.12–20.
- Parveen, N., Naik, S.C.S., Vanapalli, K.R. and Sharma, H.B., 2024. Bioplastic packaging in circular economy: A systems-based policy approach for multi-sectoral challenges. *Science of the Total Environment*, 945(1), pp.173893–173910.
- Piergiorganni, L. and Limbo, S., 2016. Food packaging materials. In: L. Piergiorganni and S. Limbo (eds.) *Food Packaging Materials*. Springer, Basel, pp.33–49.
- Prata, J.C., da Costa, J.P., Lopes, I., Duarte, A.C. and Rocha-Santos, T., 2020. Environmental exposure to microplastics: An overview on possible human health effects. *Science of the Total Environment*, 702(1), pp.134455–134470.
- Puls, J., Wilson, S.A. and Höltzer, D., 2011. Degradation of cellulose acetate-based materials: A review. *Journal of Polymers and the Environment*, 19(1), pp.152–165.
- Raddadi, N. and Fava, F., 2019. Biodegradation of oil-based plastics in the environment: existing knowledge and needs of research and innovation. *Science of the Total Environment*, 679(1), pp.148–158. [DOI]
- Rajendran, S., Al-Samyda, A., Palani, G., Trilaksana, H., Sathish, T., Giri, J., Saravanan, R., Lalvani, J.I.J. and Nasri, F., 2025. Replacement of petroleum based products with plant-based materials, green and sustainable energy — a review. *Engineering Reports*, 7(4), pp.1–22.
- Ray, U., Zhu, S., Pang, Z. and Li, T., 2021. Mechanics design in cellulose-enabled high-performance functional materials. *Advanced Materials*, 33(28), pp.1–15. [DOI]
- Ren, H., Huang, Y., Yang, W., Ling, Z., Liu, S., Zheng, S., Li, S., Wang, Y., Pan, L., Fan, W. and Zheng, Y., 2024. Emerging nanocellulose from agricultural waste: recent advances in preparation and applications in biobased food packaging. *International Journal of Biological Macromolecules*, 245(3), pp.1–25. [DOI]
- Revue, M.B., 2021. *Construction Materials: Geology, Production and Applications*. Springer Nature, pp.1–420. [DOI]
- Riseh, R.S., 2024. Advancing agriculture through bioresource technology: the role of cellulose-based biodegradable mulches. *International Journal of Biological Macromolecules*, 255(2), pp.1–18. [DOI]
- Ritzen, L., Sprecher, B., Bakker, C.A. and Balkenende, R., 2024. Sustainability of bio-based polyethylene. *Journal of Cleaner Production*, 415(1), pp.1–12.
- Rochman, C.M., 2018. Microplastics research — from sink to source. *Science*, 360(6384), pp.28–29. [DOI]
- Romão, S., Bettencourt, A. and Ribeiro, I.A., 2022. Novel features of cellulose-based films as sustainable alternatives for food packaging. *Polymers*, 14(22), pp.1–20. [DOI]
- Rubin, B.S., 2011. Bisphenol A: an endocrine disruptor with widespread exposure and multiple effects. *The Journal of Steroid Biochemistry and Molecular Biology*, 127(1–2), pp.27–34. [DOI]
- Saini, H. and Ledwani, L., 2024. A review on application of green materials in different construction systems, their processing, surface modification, testing and certification. *MRS Energy & Sustainability*, 11(2), pp.267–303. [DOI]
- Salimi, M., El Idrissi, A., Channab, B.E., Essamlali, Y., Firouzabadi, A.G., Beygi, M., Zahouily, M. and Motamedi, E., 2024. Cellulose-based controlled release fertilizers for sustainable agriculture: recent trends and future perspectives. *Cellulose*, 31(4), pp.1–48. [DOI]
- Salleh, K.M., Armir, N.A.Z., Mazlan, N.S.N., Wang, C. and Zakaria, S., 2021. Cellulose and its derivatives in textiles: primitive application to current trend. In: *Fundamentals of Natural Fibres and Textiles*. Woodhead Publishing, pp.33–63. [DOI]
- Saravia, J., You, D., Thevenot, P., Lee, G.I., Shrestha, B., Lomnicki, S. and Cormier, S.A., 2014. Early-life exposure to combustion-derived particulate matter causes pulmonary immunosuppression. *Mucosal Immunology*, 7(3), pp.694–704. [DOI]
- Schirmeister, C.G. and Mühlaupt, R., 2022. Closing the carbon loop in the circular plastics economy. *Macromolecular Rapid Communications*, 43(13), pp.1–10.
- Shaghaleh, H., Xu, X. and Wang, S., 2018. Current progress in production of biopolymeric materials based on cellulose, cellulose nanofibers, and cellulose derivatives. *RSC Advances*, 8(2), pp.825–842. [DOI]
- Shen, L., Haufe, J. and Patel, M.K., 2009. Product overview and market projection of emerging bio-based plastics PRO-BIP 2009. *Journal of Industrial Ecology*, 13(4), pp.1–245.
- Sikorska, W., Musiol, M., Zawidlak-Węgrzyńska, B. and Ryzd, J., 2021.

- End-of-life options for (bio)degradable polymers in the circular economy. *Advances in Polymer Technology*, 2021(1), pp.1–18. [DOI]
- Siró, I. and Plackett, D., 2010. Microfibrillated cellulose and new nanocomposite materials: a review. *Cellulose*, 17(3), pp.459–494. [DOI]
- Skrzypczak, D., Izydorczyk, G., Taf, R., Moustakas, K. and Chojnacka, K., 2023. Cellulose-based fertilizers for sustainable agriculture: effective methods for increasing crop yield and soil health. *Industrial Crops and Products*, 205(1), pp.1–12. [DOI]
- Slezak, R., Krzyszek, L., Puchalski, M., Krucińska, I. and Sitarski, A., 2023. Degradation of bio-based film plastics in soil under natural conditions. *Science of the Total Environment*, 866(1), pp.1–10. [DOI]
- Song, J.H., Murphy, R.J., Narayan, R. and Davies, G.B.H., 2009. Biodegradable and compostable alternatives to conventional plastics. *Philosophical Transactions of the Royal Society B: Biological Sciences*, 364(1526), pp.2127–2139. [DOI]
- Sustainable Plastics, 2024. *Nigeria to Ban Single-Use Plastics from 2025*. Retrieved April 24, 2025, from <https://www.sustainableplastics.com/news/nigeria-ban-single-use-plastics-2025>
- Tamo, A.K., 2024. Nanocellulose-based hydrogels as versatile materials with interesting functional properties for tissue engineering applications. *Journal of Materials Chemistry B*, 12(32), pp.7692–7759. [DOI]
- Taniguchi, S., Colabuono, F.I., Dias, P.S., Oliveira, R., Fisner, M., Turra, A., Izar, G.M., Abessa, D.M., Saha, M. and Hosoda, J., 2016. Spatial variability in persistent organic pollutants and polycyclic aromatic hydrocarbons found in beach-stranded pellets along the coast of the state of São Paulo, southeastern Brazil. *Marine Pollution Bulletin*, 106(1–2), pp.87–94. [DOI]
- Taokaew, S. and Kriangkrai, W., 2022. Recent progress in processing cellulose using ionic liquids as solvents. *Polysaccharides*, 3(4), pp.671–691. [DOI]
- Thompson, R.C., Moore, C.J., Vom Saal, F.S. and Swan, S.H., 2009. Plastics, the environment and human health: current consensus and future trends. *Philosophical Transactions of the Royal Society B: Biological Sciences*, 364(1526), pp.2153–2166. [DOI]
- Thompson, R.C., Olsen, Y., Mitchell, R.P., Davis, A., Rowland, S.J., John, A.W., McGonigle, D. and Russell, A.E., 2004. Lost at sea: where is all the plastic? *Science*, 304(5672), pp.838–838. [DOI]
- Tsuji, H., 2013. Poly (lactic acid). In: *Bio-Based Plastics: Materials and Applications*. Wiley Publishing, pp.171–239.
- UAE Stories, 2024. *UAE's Single-Use Plastic Ban Begins: Here's What You Need to Know!*. Retrieved April 24, 2025, from <https://uaestories.com/uaes-single-use-plastic-ban-begins-heres-what/>
- UNEP, 2018. *From Birth to Ban: A History of the Plastic Shopping Bag*. Retrieved April 24, 2025, from <https://www.unep.org/news-and-stories/story/birth-ban-history-plastic-shopping-bag>
- Van Schoubroeck, S., Van Dael, M., Van Passel, S. and Malina, R., 2018. A review of sustainability indicators for biobased chemicals. *Renewable and Sustainable Energy Reviews*, 94(1), pp.115–126. [DOI]
- Varma, R.S., 2019. Biomass-derived renewable carbonaceous materials for sustainable chemical and environmental applications. *ACS Sustainable Chemistry & Engineering*, 7(7), pp.6458–6470. [DOI]
- Verma, S.K., Prasad, A. and Katiyar, V., 2024. State of art review on sustainable biodegradable polymers with a market overview for sustainability packaging. *Materials Today Sustainability*, 24(1), pp.1–15. [DOI]
- Wang, J., Gardner, D.J., Stark, N.M., Bousfield, D.W., Tajvidi, M. and Cai, Z., 2018. Moisture and oxygen barrier properties of cellulose nanomaterial-based films. *ACS Sustainable Chemistry & Engineering*, 6(1), pp.49–70. [DOI]
- Wang, J., Wang, L., Gardner, D.J., Shaler, S.M. and Cai, Z., 2021. Towards a cellulose-based society: opportunities and challenges. *Cellulose*, 28(8), pp.4511–4543. [DOI]
- Wang, L., Wang, L., Chang, Q., Dong, J., Sun, R., Yang, S., Fu, J., Feng, C., Yang, L. and Zhang, Y., 2017. Effects of di-(2-ethylhexyl) phthalate on microbial biomass carbon and microbial community structural diversity in a Mollisol. *European Journal of Soil Science*, 68(6), pp.897–908. [DOI]
- Wang, Y., Wang, Z., Lin, Y., Qin, Y., He, R., Wang, M., Sun, Q. and Peng, Y., 2024. Nanocellulose from agro-industrial wastes: a review on sources, production, applications, and current challenges. *Food Research International*, 178(1), pp.1–18. [DOI]
- Wright, S.L., Thompson, R.C. and Galloway, T.S., 2013. The physical impacts of microplastics on marine organisms: a review. *Environmental Pollution*, 178(1), pp.483–492. [DOI]
- Wu, F., Misra, M. and Mohanty, A.K., 2021. Challenges and new opportunities on barrier performance of biodegradable polymers for sustainable packaging. *Progress in Polymer Science*, 117(1), pp.1–25. [DOI]
- Xiao-Ju, Y., Huan, H., Ying, P., Xiao-Meng, W., Zhan-Qi, G., Shao-Gui, Y. and Chen, S., 2012. Determination of organophosphorus flame retardants in surface water by solid phase extraction coupled with gas chromatography–mass spectrometry. *Chinese Journal of Analytical Chemistry*, 40(12), pp.1693–1697. [DOI]
- Yadav, N. and Hakkarainen, M., 2021. Degradable or not? Cellulose acetate as a model for complicated interplay between structure, environment and degradation. *Chemosphere*, 265(1), pp.1–12.
- Yan, Z., Liu, Y., Yan, K., Wu, S., Han, Z., Guo, R., Chen, M., Yang, Q., Zhang, S. and Chen, J., 2017. Bisphenol analogues in surface water and sediment from the shallow Chinese freshwater lakes: occurrence, distribution, source apportionment, and ecological and human health risk. *Chemosphere*, 184(1), pp.318–328. [DOI]
- Yaradoddi, J.S., Banapurmath, N.R., Ganachari, S.V., Soudagar, M.E.M., Mubarak, N.M., Hallad, S., Hugar, S. and Fayaz, H., 2020. Biodegradable carboxymethyl cellulose based material for sustainable packaging application. *Scientific Reports*, 10(1), pp.1–12. [DOI]
- Yekta, R., Abedi-Firoozjah, R., Azimi Salim, S., Khezerlou, A. and Abdolmaleki, K., 2023. Application of cellulose and cellulose derivatives in smart/intelligent bio-based food packaging. *Cellulose*, 30(16), pp.9925–9953. [DOI]
- Zeghal, E., Vaksmaa, A., Vielfaure, H., Boekhout, T. and Niemann, H., 2021. The potential role of marine fungi in plastic degradation — a review. *Frontiers in Marine Science*, 8(1), pp.1–15. [DOI]
- Zhan, C., 2024. Microbial decomposition and soil health: mechanisms and ecological implications. *Molecular Soil Biology*, 15(1), pp.1–20. [DOI]
- Zhao, D., Zhu, Y., Cheng, W., Chen, W., Wu, Y. and Yu, H., 2021. Cellulose-based flexible functional materials for emerging intelligent electronics. *Advanced Materials*, 33(28), pp.1–15. [DOI]